



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification<sup>5</sup> :</b> <b>B29D 11/00, C08F 30/08</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 94/03324</b> <b>(43) International Publication Date:</b> 17 February 1994 (17.02.94)
<b>(21) International Application Number:</b> PCT/US93/05827 <b>(22) International Filing Date:</b> 17 June 1993 (17.06.93) <b>(30) Priority data:</b> 07/924,214                      3 August 1992 (03.08.92)                      US <b>(71) Applicant:</b> BAUSCH & LOMB INCORPORATED [US/ US]; Patent Law Department, One Lincoln First Square, P.O. Box 54, Rochester, NY 14601-0054 (US). <b>(72) Inventors:</b> BAWA, Rajan, Sohansingh ; 7 Chesfield Look- out, Fairport, NY 14450 (US). LAI, Yu-Chin ; 23 Cop- per Woods, Pittsford, NY 14534 (US). NANDU, Ma- hendra, Premji ; 218 Guinevere Drive, Rochester, NY 14626 (US).		<b>(74) Agents:</b> THOMAS, John, E. et al.; Bausch & Lomb Incor- porated, One Lincoln First Square, P.O. Box 54, Roches- ter, NY 14601-0054 (US). <b>(81) Designated States:</b> AU, BB, BG, BR, CA, CZ, FI, HU, JP, KP, KR, LK, MG, MN, MW, NO, NZ, PL, RO, RU, SD, SK, UA, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> PROCESS FOR MAKING SILICONE CONTAINING HYDROGEL LENSES  <b>(57) Abstract</b>  A process for preparing silicone hydrogel contact lenses where machining operations are employed to produce a lens hav- ing a desired final shape comprises: providing a monomeric mixture comprising a silicone-containing monomer, a hydrophilic monomer and an organic diluent; charging the mixture to a mold and curing the formulation in the mold to obtain a shaped arti- cle; removing organic diluent from the shaped article to improve machineability of the article; and machining the shaped article to obtain a contact lens having a desired configuration.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

PROCESS FOR MAKING SILICONE CONTAINING  
HYDROGEL LENSES

BACKGROUND OF THE INVENTION

The present invention relates to an improved process for making silicone hydrogel lenses.

Hydrogels represent a desirable class of materials for contact lenses. A hydrogel is a hydrated cross-linked polymeric system that contains water in an equilibrium state. Hydrogel lenses offer relatively high oxygen permeability as well as desirable biocompatibility and comfort.

Conventional hydrogel lenses are prepared from monomeric mixtures predominantly containing hydrophilic monomers such as 2-hydroxyethyl methacrylate or N-vinyl pyrrolidone. Oxygen permeability of these conventional hydrogel materials relates to the water content of the materials. More recently, it has been desired to increase the oxygen permeability of hydrogel lenses by employing silicone-containing monomers in the hydrogel formulations since silicone based materials have higher oxygen permeability than water. Silicone hydrogels (i.e., hydrogels containing silicone) are usually prepared by polymerizing a mixture containing at least one silicone-containing monomer and at least one hydrophilic monomer. Either the silicone-containing monomer or the hydrophilic monomer may function as a crosslinking agent (a crosslinker being defined as a monomer having multiple polymerizable functionalities) or a separate crosslinker may be employed.

Various processes are known for curing a monomeric mixture in the production of contact lenses, including spincasting and static casting. Spincasting methods are disclosed in U.S. Patent Nos. 3,408,429 and 3,660,545, and static casting methods are disclosed in U.S. Patent Nos. 4,113,224 and 4,197,266. Curing of the monomeric mixture is often followed by a machining operation in order to provide a contact lens having a desired final configuration.

According to several known techniques for manufacturing contact lenses, the casting process may yield a shaped article having the desired posterior and anterior lens surfaces. For example, in static casting processes, a monomeric mixture can be charged to a mold comprising a first mold section including a surface for forming a desired anterior lens surface and a second mold section including a surface for forming a desired posterior lens surface. In spincasting processes, the monomeric mixture can be charged to an open mold having a surface for forming a desired anterior lens surface, and a desired posterior lens surface is formed from rotation of the mold. However, machining operations, subsequent to the curing of the article, may still be necessary to provide a contact lens more suitable for placement on the eye. Such machining operations include lathe cutting the lens to obtain a desired edge, buffing the lens edge or polishing the lens edge or surface.

In other known manufacturing techniques, the casting process may yield a shaped article which does not have the desired anterior and/or posterior lens surfaces. Accordingly, the casting process is followed by a machining operation to form a desired

lens surface. As an example, U.S. Patent No. 4,555,732 discloses a process where an excess of a monomeric mixture is cured by spincasting in a mold to form a shaped article having an anterior lens surface and a relatively large thickness, and the posterior surface of the cured spincast article is subsequently lathe cut to provide a contact lens having the desired thickness and posterior lens surface. Further machining operations may follow the lathe cutting of the lens surface, such as the previously described edge finishing operations.

However, difficulties have been encountered in attempts to employ such methods which involve machining operations in the production of silicone hydrogel contact lenses. For example, silicone hydrogel articles generally are more difficult to machine than conventional hydrogel articles, as hydrogels prepared from silicone-containing monomers tend to be softer and more rubbery than hydrogels prepared from only the conventional monomers, especially when cast with a diluent.

#### SUMMARY OF THE INVENTION

The present invention provides a process for preparing silicone hydrogel contact lenses where machining operations are employed to produce a lens having a desired final shape. The process comprises:

- providing a monomeric mixture comprising a silicone-containing monomer, a hydrophilic monomer and an organic diluent;

- charging the mixture to a mold and curing the mixture in the mold to obtain a shaped article;


removing organic diluent from the shaped article to improve machineability of the article; and

machining the shaped article to obtain a contact lens having a desired configuration.

#### DETAILED DESCRIPTION OF THE INVENTION

Any known silicone hydrogel formulation including at least one silicone-containing monomer and at least one hydrophilic monomer may be used in the process of this invention, as will be apparent to one skilled in the art. The monomers may be added to the monomeric mixture from which a shaped article is obtained as monomers or prepolymers. Thus, it is understood that the terms "silicone-containing monomers" and "hydrophilic monomers" include prepolymers. Examples of silicone-containing monomers may be found in United States Patent Nos. 4,136,250; 4,153,641; 4,740,533; 5,034,461; and 5,070,215.

Further examples of suitable silicone-containing monomers are bulky polysiloxanylalkyl (meth)acrylic monomers represented by formula (I):



wherein:

X denotes -O- or -NR-;


each R independently denotes hydrogen or methyl;

each R<sup>1</sup> independently denotes a lower alkyl radical or a phenyl radical; and

f is 1 or 3 to 10.

Such bulky monomers include methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanyl methylmethacrylate, tris(trimethylsiloxy) methacryloxy propylsilane, phenyltetramethyl-disiloxanylethyl acetate, and methyldi(trimethylsiloxy)methacryloxymethyl silane.

One preferred class of silicone-containing monomers is a poly(organosiloxane) prepolymer represented by formula (II):



wherein:

each A' independently denotes an activated unsaturated group, such as an ester or amide of an acrylic or a methacrylic acid;


each of R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup> and R<sup>6</sup> are independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;

R<sup>7</sup> denotes a divalent hydrocarbon radical having from 1 to 22 carbon atoms; and

n is 0 or an integer greater than or equal to 1.

Another preferred class of silicone containing monomers includes silicone-containing vinyl

carbonate or vinyl carbamate monomers of formula (III):



wherein:

Y' denotes -O-, -S- or -NH-;




R<sup>Si</sup> denotes a silicone-containing organic radical;

R<sup>8</sup> denotes hydrogen or methyl;

d is 1, 2, 3 or 4; and


q is 0 or 1.

Suitable silicone-containing organic radicals R<sup>Si</sup> include the following:



wherein:

R<sup>10</sup> denotes



R<sup>11</sup> denotes an alkyl radical or a fluoroalkyl radical having 1 to 6 carbon atoms;


e is 1 to 200;

n' is 1, 2, 3 or 4; and

m' is 0, 1, 2, 3, 4 or 5.



The silicone-containing vinyl carbonate or vinyl carbamate monomers specifically include: 1,3-bis[4-vinyloxycarbonyloxy)but-1-yl]tetramethyldisiloxane; 3-(trimethylsilyl)propyl vinyl carbonate; 3-(vinyloxycarbonylthio)propyl-[tris(trimethylsiloxy)silane]; 3-[tris(trimethylsiloxy)silyl] propyl vinyl carbamate; 3-[tris(trimethylsiloxy)silyl] propyl allyl carbamate; 3-[tris(trimethylsiloxy)silyl] propyl vinyl carbonate; t-butyl dimethylsiloxyethyl vinyl carbonate; trimethylsilylethyl vinyl carbonate; trimethylsilylmethyl vinyl carbonate; and "V<sub>2</sub>D<sub>25</sub>",



A further preferred class of silicone-containing monomers includes monomers of the following formulae:



wherein:


D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

\* denotes a urethane or ureido linkage;

a is at least 1;

A denotes a divalent polymeric radical of formula (VI):




wherein:

each  $\text{R}^{\text{S}}$  independently denotes an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon atoms which may contain ether linkages between carbon atoms;

m is at least 1; and

p provides a moiety weight of 400 to 10,000;

each of E and E' independently denotes a polymerizable unsaturated organic radical represented by formula (VII):



wherein:

$\text{R}^{12}$  is hydrogen or methyl;

$\text{R}^{13}$  is hydrogen, an alkyl radical having 1 to 6 carbon atoms, or a  $-\text{CO}-\text{Y}-\text{R}^{15}$  radical wherein Y is  $-\text{O}-$ ,  $-\text{S}-$  or  $-\text{NH}-$ ;

$\text{R}^{14}$  is a divalent alkylene radical having 1 to 10 carbon atoms;

$\text{R}^{15}$  is a alkyl radical having 1 to 12 carbon atoms;

X denotes  $-\text{CO}-$  or  $-\text{OCO}-$ ;

Z denotes  $-\text{O}-$  or  $-\text{NH}-$ ;

Ar denotes an aromatic radical having 6 to 30 carbon atoms;


w is 0 to 6;

x is 0 or 1;

y is 0 or 1; and

z is 0 or 1.

A preferred urethane monomer is represented by formula (VIII):



wherein  $\text{R}^{16}$  is a diradical of a diisocyanate after removal of the isocyanate group, such as the diradical of isophorone diisocyanate, and each  $\text{E}''$  is a group represented by:



The silicone-containing monomers may be copolymerized with a wide variety of hydrophilic monomers to produce silicone hydrogel lenses. Suitable hydrophilic monomers include: unsaturated

carboxylic acids, such as methacrylic and acrylic acids; acrylic substituted alcohols, such as 2-hydroxyethylmethacrylate and 2-hydroxyethylacrylate; vinyl lactams, such as N-vinyl pyrrolidone; and acrylamides, such as methacrylamide and N,N-dimethylacrylamide. Still further examples are the hydrophilic vinyl carbonate or vinyl carbamate monomers disclosed in U.S. Patent Nos. 5,070,215, and the hydrophilic oxazolone monomers disclosed in U.S. Patent No. 4,910,277. Other suitable hydrophilic monomers will be apparent to one skilled in the art.

An organic diluent is included in the initial monomeric mixture. As used herein, the term "organic diluent" encompasses organic compounds which minimize incompatibility of the components in the initial monomeric mixture and are substantially nonreactive with the components in the initial mixture. Additionally, the organic diluent serves to minimize phase separation of polymerized products produced by polymerization of the monomeric mixture. Also, the organic diluent will generally lower the glass transition temperature of the reacting polymeric mixture which allows for a more efficient curing process, and which ultimately results in a more uniformly polymerized product. Uniformity of the initial monomeric mixture and the polymerized product are of particular concern for silicone hydrogels primarily due to the inclusion of silicone-containing monomers.

Contemplated organic diluents include: monohydric alcohols, with C<sub>6</sub>-C<sub>10</sub> straight-chained aliphatic monohydric alcohols, such as n-hexanol and n-nonanol, being especially preferred; diols, such as ethylene glycol; polyols, such as glycerin;

ethers, such as diethylene glycol monoethyl ether; ketones, such as methyl ethyl ketone; esters, such as methyl enanthate; and hydrocarbons, such as toluene. Preferably, the organic diluent is sufficiently volatile to facilitate its removal from a cured article by evaporation at or near ambient pressure. Other suitable organic diluents would be apparent to a person of ordinary skill in the art.

The organic diluent is included in an amount effective to provide the desired effect. Generally, the diluent is included at 5 to 60% by weight of the monomeric mixture, with 10 to 50% by weight being especially preferred.

According to the present process, the monomeric mixture, comprising at least one hydrophilic monomer, at least one silicone-containing monomer and the organic diluent, is cured by conventional methods such as static casting or spincasting.

Subsequently, a sufficient amount of organic diluent is removed from the cured article to improve the machineability of the article. Applicants discovered that although the inclusion of the organic diluent can minimize the aforementioned problems associated with monomer incompatibility, phase separation or nonuniform polymerization, excess residual diluent can render normally soft silicone hydrogel articles even tackier or more rubbery and more difficult to machine; in fact, machining of the cured article may be precluded altogether. Surprisingly, the process according to the present process provides removal of organic diluent from the cured article without deformation of the article, such as warping of the lens.

The organic diluent is preferably removed by evaporation at or near ambient pressure, and an

elevated temperature can be employed to shorten the time necessary to evaporate the diluent. The time, temperature and pressure conditions for the removal step will vary depending on such factors as the volatility of the diluent and the specific monomeric components, as can be readily determined by one skilled in the art. According to a preferred embodiment, the temperature employed in the removal step is at least 50°C, and more preferably, at least 55°C. Preferably, the cured article after the diluent removal step will contain no more than 20% by weight of diluent, and preferably, no more than 5% by weight.

Following removal of the organic diluent, the shaped article is machined by various processes known in the art. The machining step includes lathe cutting a lens surface, lathe cutting a lens edge, buffing a lens edge or polishing a lens edge or surface. The present process is particularly advantageous for processes wherein a lens surface is lathe cut, since machining of a lens surface is especially difficult when the surface is tacky or rubbery.

Generally, such machining processes are performed before the article is released from a mold part. After the machining operation, the lens can be released from the mold part and hydrated. Alternately, the article can be machined after removal from the mold part and then hydrated.

Representative formulations are listed below.

FORMULATION A

<u>Component</u>	<u>Parts by Weight</u>
TRIS-VC	55
NVP	30
V <sub>2</sub> D <sub>25</sub>	15
VINAL	1
n-nonanol	15
Darocur	0.2
tint agent	0.05

FORMULATION B

<u>Component</u>	<u>Parts by Weight (or Weight Percent)</u>
IDS3H	35
Tris	35
DMA	39
MAA	1
n-hexanol	40
TXN	0.1 %
MDEA	0.2 %
tint agent	0.007 %

FORMULATION C

<u>Component</u>	<u>Parts by Weight (or Weight Percent)</u>
IDS3H	30
Tris	30
NVP	27
DMA	9
VDMO	1
HEMAvc	0.15
n-hexanol	30
Darocur	0.5 %
tint agent	0.03 %

FORMULATION D

<u>Component</u>	<u>Parts by Weight (or Weight Percent)</u>
IDS3H	30
Tris	30
NVP	27
DMA	9
VDMO	1
HEMAvc	0.15
n-nonanol	30
Darocur	0.5 %
tint agent	0.03 %



FORMULATION E

<u>Component</u>	<u>Parts by Weight (or Weight Percent)</u>
IDS3H	35
Tris	35
DMA	48
MAA	1
n-hexanol	40
TXN	0.1 %
MDEA	0.2 %
tint agent	0.007 %

The following materials are designated above.

Darocur	Darocur-1173, a UV initiator
DMA	N,N-dimethylacrylamide
HEMAvc	methacryloxyethyl vinyl carbonate
IDS3H	a urethane prepolymer derived from isophorone diisocyanate, diethylene glycol and alpha,omega-bis(hydroxybutyldimethylsilyl) polysiloxane and end-capped with 2-hydroxyethy methacrylate (described in U.S. Patent No. 5,034,461)
MAA	methacrylic acid
MDEA	methyl diethanolamine
NVP	N-vinyl pyrrolidone
tint agent	1,4-bis[4-(2-methacryloxyethyl)phenylamino]anthraquinone
TRIS	tris(trimethylsiloxy)silylpropyl methacrylate

TRIS-VC	tris(trimethylsiloxy)silylpropyl vinyl carbamat
TXN	thioxanthone
V <sub>2</sub> D <sub>25</sub>	a silicone-containing vinyl carbonate as previously described
VDMO	2-vinyl-4,4-dimethyl-2-oxazoline-5- one
VINAL	N-vinyloxycarbonyl alanine

The following examples further illustrate preferred embodiments of the present invention.

#### EXAMPLE 1

Under an inert nitrogen atmosphere, 20- $\mu$ l of Formulation A was injected onto a clean open concave mold made of Barex resin (a rubber modified copolymer of acrylonitrile and methylacrylate). The mold was spun for about 5 minutes at 320 rpm in the presence of UV light (1-2.5 mW/cm<sup>2</sup> as measured by Black ray UV meter) and exposed to UV light for about 30 additional minutes to complete the cure.

The lenses were maintained at 60°C for 3 hours in a forced air oven to remove n-nonanol. Subsequently, the lenses were edged and ball buffed at 1000 rpm for 6 seconds with a force of 25 g while still in the mold. The lenses were manually released from the molds in water at 50°C, and extracted in isopropanol at room temperature for a minimum of 48 hours. The lenses were then extracted with water at about 85°C for four hours. Finally, the lenses were autoclaved in vials containing buffered saline.

## EXAMPLE 2

Under an inert nitrogen atmosphere, 30- $\mu$ l of Formulation B was injected onto a clean open concave Barex resin mold. The mold was spun for about 15 minutes at 341 rpm in the presence of UV light (1-2.5 mW/cm<sup>2</sup> as measured by Black ray UV meter) and exposed to UV light for about 30 additional minutes to complete the cure.

The lenses were left overnight at room temperature to remove n-hexanol. Subsequently, the lenses were edged and ball buffed at 1000 rpm for 3 seconds with a force of 130 g while still in the mold. The lenses were released from the molds in an ethanol/water medium, extracted in ethanol at room temperature for a minimum of 48 hours, and then extracted with water at 80°C for 4 hours. Finally, the lenses were cleaned and heat disinfected using unpreserved buffered saline.

## EXAMPLE 3

Under an inert nitrogen atmosphere, 45- $\mu$ l of Formulation C was injected onto a clean Barex resin concave mold half and covered with a polypropylene resin convex mold half. The mold halves were compressed at a pressure of 70 psi and the mixture was cured for about 15 minutes in the presence of UV light (6-11 mW/cm<sup>2</sup> as measured by Spectronic UV meter), and the mold was exposed to UV light for about 5 additional minutes.

The top mold half was removed and the lenses were maintained at 60°C for 3 hours in a forced air oven to remove n-hexanol. Subsequently, the lens edges were lathe cut and ball buffed for 10 seconds

at 2300 rpm with a force of 60 g. The lenses were manually released from the molds in water at 50°C, and then extracted in isopropanol at room temperature for a minimum of 48 hours, followed by extraction in water at about 85°C for 4 hours. Finally, the lenses were disinfected using unpreserved buffered saline.

#### EXAMPLE 4

Under an inert nitrogen atmosphere, 80- $\mu$ l of Formulation C was injected onto a clean open concave Barex resin mold. The mold was spun for about 20 minutes at 400 rpm in the presence of UV light (6-10 mW/cm<sup>2</sup> as measured by Spectronic UV meter) and exposed to UV light for about 12 additional minutes.

The shaped articles were maintained at 60°C for 3 hours in a forced air oven to remove n-hexanol. Subsequently, the posterior surfaces of the articles were lathe cut, then the lenses were polished for 30 seconds. The lenses were manually released from the molds in water at 50°C, extracted in isopropanol for a minimum of 48 hours, followed by extraction in water at about 85°C for 4 hours. Finally, the lenses were autoclaved in buffered saline.

#### EXAMPLE 5

The procedure of Example 4 was followed except that Formulation D, including 30 parts by weight of n-nonanol, was employed in place of Formulation C.

## EXAMPLE 6

Each of Formulations X-1, X-2 and X-3 (containing n-hexanol at 10, 15 and 20 parts by weight, respectively) were static cast in flat polypropylene disc molds and cured with UV light. The cured flat discs were inspected. The discs cast from Formulations X-2 and X-3, which contained 15 and 20 parts by weight of n-hexanol, respectively, appeared too tacky to permit machining of the edges due to excess residual n-hexanol, whereas the discs cast from Formulation X-1, which contained only 10 parts by weight of n-hexanol, appeared non-tacky.

FORMULATIONS X-1, X-2, X-3

<u>Component</u>	<u>Parts by Weight (or Weight Percent)</u>
IDS3H	35
Tris	35
DMA	30
n-hexanol	10, 15, 20
BME*	0.2 %
*BME	benzoin methyl ether, a UV initiator

## EXAMPLE 7

Lenses were spincoated from Formulation A (containing 15 parts by weight n-nonanol) following the procedure of Example 1. The spincoated lenses, remaining in the mold, were placed in a forced air oven maintained at temperatures of 50°C, 55°C and 60°C.

For the lenses dried at 55°C and 60°C, two lenses, remaining in the mold, were removed from the oven at each interval of 0 (control), 1, 2, 3, 4, 5, 6 and 24 hours, and extracted with 2 ml of isopropanol for a minimum of 12 hours. For the lenses dried at 50°C, two lenses, remaining in the mold, were removed at each interval of 0 (control), 1, 6 and 24 hours, and each sample was extracted with 2 ml of isopropanol for a minimum of 12 hours. Samples of each isopropanol extract (0.1 µl) were obtained and subjected to capillary gas chromatography to determine n-nonanol content.

The percentage of n-nonanol in the samples, based on the control, was less than 5% after a drying time of 2 hours at 55°C and 60°C and after a drying time of 6 hours at 50°C.

## EXAMPLE 8

Lenses were again spincoated from Formulation A (containing 15 parts by weight n-nonanol) following the procedure of Example 1. The spincoated lenses, remaining in the mold, were placed in a forced air oven maintained at a temperature of 55°C. Ten molds were removed at each interval of 1, 2, 3, 4, 5 and 6 hours and 24 hours (as a control), and the lenses were edged following the procedure of Example 1.

The edges of lenses that were maintained at ~~55°C for 1 hour~~ appeared rough and chipped after edging, whereas the lenses that were maintained at 55°C for 24 hours could be edged satisfactorily. The lenses that exhibited poor edging contained excess residual n-nonanol in the lenses. Each of the lenses that were maintained at 55°C for 2 hours or longer edged comparatively with the lenses maintained at 55°C for 24 hours. Accordingly, sufficient diluent was removed from the spincast lenses to machine edge the lenses by maintaining the lenses at 55°C for at least 2 hours. Based on the data from Example 7, removal of n-nonanol to below 5% was sufficient to provide satisfactory edging.

While certain preferred embodiments have been described, it is understood that the invention is not limited thereto and modifications and variations would be evident to a person of ordinary skill in the art.

We claim:

1. A process for preparing silicone hydrogel contact lenses, said process comprising:

(a) providing a monomeric mixture comprising a silicone-containing monomer, a hydrophilic monomer and an organic diluent;

(b) charging the monomeric mixture to a mold and curing the formulation in the mold to obtain a shaped article;

(c) removing diluent from the shaped article to improve machineability of the shaped article; and

(d) machining the shaped article to obtain a contact lens having a desired configuration.

2. The process according to claim 1, wherein the monomeric mixture is charged to a mold comprising a first mold section including a surface for forming an anterior lens surface and a second mold section including a surface for forming a posterior lens surface.

3. The process according to claim 1, wherein the monomeric mixture is cured by spincoating.

4. The process according to claim 1, wherein step (d) comprises machining a lens surface to a desired configuration.

5. The process according to claim 4, wherein the machining comprises lathe cutting a posterior lens surface.



6. The process according to claim 4, wherein the machining comprises lathe cutting an anterior lens surface.

7. The process according to claim 4, wherein the machining comprises polishing a lens surface.

8. The process according to claim 1, wherein step (d) comprises machining an edge of a lens-shaped article to a desired edge configuration.

9. The process according to claim 8, wherein the machining comprises lathe cutting the edge.

10. The process according to claim 8, wherein the machining comprises buffing the edge.

11. The process according to claim 1, comprising:

- (a) providing said monomeric mixture;
- (b) charging an excess of said mixture to a mold including a concave surface for forming a desired anterior lens surface and spincast curing the formulation in the mold to obtain a shaped article having the desired anterior lens surface;
- (c) removing diluent from the shaped article to improve machineability of the article; and
- (d) lathe cutting the posterior surface of the article to obtain a contact lens with a desired thickness.

12. The process according to claim 1, comprising:

- (a) providing said monomeric mixture;
- (b) charging said monomeric mixture to a mold, wherein said mold comprises a first mold section including a surface for forming an anterior lens surface and a second mold section including a surface for forming a posterior lens surface, and curing said formulation in the mold to obtain a lens-shaped article having the anterior and posterior lens surfaces;
- (c) removing diluent to improve machineability of the article; and
- (d) machining the edge of the article to obtain a contact lens with a desired edge configuration.

13. The process according to claim 1, comprising:

- (a) providing said monomeric mixture;
- (b) charging said monomeric mixture to a mold including a negative molding surface for forming a desired anterior lens surface and spincast curing the monomeric mixture in the mold to obtain a lens-shaped article having the desired anterior lens surface and a desired posterior lens surface;
- (c) removing diluent to improve machineability of the article; and
- (d) machining the edge of the article to obtain a contact lens with a desired edge configuration.

14. The process according to claim 1, further comprising hydrating the lens obtained from step (d).

15. The process according to claim 1, wherein the organic diluent is an alcohol.

16. The process according to claim 15, wherein the organic diluent is selected from the group consisting of n-hexanol and n-nonanol.

17. The process according to claim 15, wherein step (c) comprises drying the shaped article at an elevated temperature.

18. The process according to claim 17, wherein the shaped article is maintained at a temperature of at least 50°C for at least 2 hours.

19. The process according to claim 1, wherein the silicone-containing monomer is selected from the group consisting of silicone-containing vinyl carbonate prepolymers and silicone-containing vinyl carbamate prepolymers.

20. The process according to claim 1, wherein the silicone-containing monomer is a silicone-containing urethane prepolymer.

21. A silicone hydrogel contact lens prepared by the process of claim 1.

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 93/05827

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (If several classification symbols apply, indicate all) *		
According to International Patent Classification (IPC) or to both National Classification and IPC		
IPC <sup>5</sup> : B 29 D 11/00, C 08 F 30/08		
<b>II. FIELDS SEARCHED</b>		
Minimum Documentation Searched <sup>7</sup>		
Classification System	Classification Symbols	
IPC <sup>5</sup>	B 29 D, C 08 F	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched <sup>8</sup>		
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT<sup>9</sup></b>		
Category <sup>10</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>
X	US, A, 4 540 761 (KAWAMURA) 10 September 1985 (10.09.85), the whole document.	1
A	---	4-12, 18, 19
A	US, A, 5 122 314 (BELLO) 16 June 1992 (16.06.92), claim 1.	1, 3
A	US, A, 4 152 508 (ELLIS) 01 May 1979 (01.05.79), claims 1, 2.	1, 4- 12, 18, 19
A	US, A, 4 139 513 (TANAKA) 13 February 1979 (13.02.79), the whole document.	1, 4- 12, 18, 19
<p>* Special categories of cited documents: <sup>10</sup></p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"Z" document member of the same patent family</p>		
<b>IV. CERTIFICATION</b>		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
23 August 1993	04. 10. 93	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	REININGER e.h.	

## ANHANG

## ANNEX

## ANNEXE

zum internationalen Recherchen-  
bericht über die internationale  
Patentanmeldung Nr.

to the International Search  
Report to the International Patent  
Application No.

au rapport de recherche inter-  
national relatif à la demande de brevet  
international n°

PCT/US 93/05827 SAE 75894

In diesem Anhang sind die Mitglieder  
der Patentfamilien der im obenge-  
nannten internationalen Recherchenbericht  
angeführten Patentdokumente angegeben.  
Diese Angaben dienen nur zur Unter-  
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family  
members relating to the patent documents  
cited in the above-mentioned inter-  
national search report. The Office is  
in no way liable for these particulars  
which are given merely for the purpose  
of information.

La présente annexe indique les  
membres de la famille de brevets  
relatifs aux documents de brevets cités  
dans le rapport de recherche inter-  
national visée ci-dessus. Les renseigne-  
ments fournis sont donnés à titre indica-  
tif et n'engagent pas la responsabilité  
de l'Office.

Im Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche		Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
US A	4540761	10-09-85	AU A1 17794/83	23-02-84
			AU B2 543235	04-04-85
			BR A 8307455	17-07-84
			CA A1 1205943	10-06-86
			CH A 664837	31-03-88
			DE T 3390130	09-08-84
			DE C2 3390130	11-08-88
			EP A1 114894	08-08-84
			EP B1 114894	27-01-88
			ES A1 524433	01-07-84
			ES A5 524433	01-08-84
			ES A1 8406743	01-11-84
			GB A0 8407392	02-05-84
			GB A1 2135476	30-08-84
			GB B2 2135476	19-03-86
			JP A2 59019918	01-02-84
			JP B4 62061928	24-12-87
			KR B1 8501868	28-12-85
			NL A 8320221	01-06-84
			NL B 184926	03-07-89
			NL C 184926	01-12-89
			PH A 18402	21-06-85
			WO A1 8400619	16-02-84
US A	5122314	16-06-92	EP A1 513315	19-11-92
			JP T2 5503898	24-06-93
			WO A1 9210357	25-06-92
US A	4152508	01-05-79	AU A1 43947/79	23-08-79
			AU B2 520158	14-01-82
			CA A1 1102485	02-06-81
			DE A1 2902324	23-08-79
			DE C2 2902324	20-08-87
			DE C2 2954547	13-10-88
			FR A1 2417782	14-09-79
			FR B1 2417782	19-07-85
			GB A1 2014591	30-08-79
			GB B2 2014591	16-06-82
			JP A2 54118455	13-09-79
			JP B4 2019925	07-05-90
			JP A2 2147613	06-06-90
			JP B4 3040060	17-06-91
US A	4139513	13-02-79	JP A2 54066853	29-03-79
			JP B4 56040324	19-09-81